


# ABDUNKLUNG



# ABDUNKLUNG



Rollo	Fläche
Vertikal	PG
Stoffbreite	

R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F						
V	5	V	4	V	2	V	5	V	1	V	4	V	2	■	2	■	2	■	2	■	2
280		300		310		305		280		300		310		305		305		305		305	

Artikel-Nr.

5170 4656 2200 5100 1568 4651 2205 2206 2652 2650 2658 2654

Rollo	Fläche
Vertikal	PG
Stoffbreite	

R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F		
■	2	V	5	V	5	■	2	V	4	■	2	V	5	■	2	V	2	V	5	V	2	V	1
200		280		305		200		300		305		305		305		310		305		310		250	

Artikel-Nr.

2484 5171 5104 2486 4650 2653 5105 2660 2202 5103 2201 1571

Rollo	Fläche
Vertikal	PG
Stoffbreite	

R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F
■	2	V	5	V	5	V	2	V	4	V	2	V	4	V	2	V	4	V	2	V	4	V	5
200		305		280		240		300		310		300		240		300		280		280		280	

Artikel-Nr.

2481 5106 5174 2204 4652 2203 4655 2661 4654 5173

Rollo	Fläche
Vertikal	PG
Stoffbreite	

R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F
■	2	V	5	V	2	V	1	V	1	V	5	■	2	V	2	■	2	V	5	V	1
200		280		310		250		250		305		200		310		305		305		250	

Artikel-Nr.

2485 5172 2208 1572 1561 5101 2482 2207 2657 5102 1570

Rollo	Fläche
Vertikal	PG
Stoffbreite	

R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F
■	2	■	1	V	1	V	2	■	1	V	1	■	2	V	4	■	2	■	2	V	2	V	2
200		200		200		230		200		200		200		300		305		305		245		230	

Artikel-Nr.



2487 1578 1582 2217 1580 1567 2483 4653 2651 2656 2220 2219

Rollo	Fläche
Vertikal	PG
Stoffbreite	

R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F	R	F
■	2	V	1	■	1	■	1	■	1	■	2	V	2	■	1	■	1	■	1	■	1	V	1
200		250		200		200		200		305		245		200		200		250		250		250	

Artikel-Nr.

2480 1560 1581 1577 1579 2659 2218 1584 1585 1583 1562



Art-Nr.	Name	Preisgruppe	Stoffbreite in mm	Gewicht g/m <sup>2</sup>	Dicke in mm	schwer entflammbar	Lichtecht	Ökotex	PVC-frei	Transmission (Tv)	Absorption (Av)	Reflektion (Rv)
1560	Colorado Blackout	1	2500	330	0,45		4-6			0%	56%	44%
1561	Colorado Blackout	1	2500	330	0,45		4-6			0%	97%	3%
1562	Colorado Blackout	1	2500	330	0,45		4-6			0%	45%	55%
1567	Colorado Blackout	1	2000	330	0,45		4-6			0%	87%	13%
1568	Colorado Blackout	1	2800	330	0,45		4-6			0%	20%	80%
1570	Colorado Blackout	1	2500	330	0,45		4-6			0%	84%	16%
1571	Colorado Blackout	1	2500	330	0,45		4-6			0%	32%	68%
1572	Colorado Blackout	1	2500	330	0,45		4-6			0%	55%	45%
1577	Colorado Blackout	1	2000	330	0,45		4-6			0%	85%	15%
1578	Colorado Blackout	1	2000	330	0,45		4-6			0%	88%	12%
1579	Colorado Blackout	1	2000	330	0,45		4-6			0%	49%	51%
1580	Colorado Blackout	1	2000	330	0,45		4-6			0%	91%	9%
1581	Colorado Blackout	1	2000	330	0,45		4-6			0%	55%	45%
1582	Colorado Blackout	1	89/127/2000	330	0,45		4-6			0%	63%	37%
1583	Colorado Blackout	1	2000/2500	330	0,45		4-6			0%	51%	49%
1584	Colorado Blackout	1	2000	330	0,45		4-6			0%	56%	44%
1585	Colorado Blackout	1	2000	330	0,45		4-6			0%	58%	42%
2200	Blackout B1	2	3100	365	0,42	•	6-7	•	•	0%	20%	80%
2201	Blackout B1	2	3100	365	0,42	•	6-7	•	•	0%	20%	80%
2202	Blackout B1	2	3100	365	0,42	•	6-7	•	•	0%	20%	80%
2203	Blackout B1	2	3100	365	0,42	•	6-7	•	•	0%	20%	80%
2204	Blackout B1	2	2400	365	0,42	•	6-7	•	•	0%	20%	80%
2205	Blackout B1	2	3100	365	0,42	•	6-7	•	•	0%	20%	80%
2207	Blackout B1	2	3100	365	0,42	•	6-7	•	•	0%	20%	80%
2208	Blackout B1	2	3100	365	0,42	•	6-7	•	•	0%	20%	80%
2217	Blackout B1	2	89 / 127 / 2300	420	0,5		>6			0%	16%	84%
2218	Blackout B1	2	89 / 127 / 2450	340	0,4		>6			0%	17%	73%
2219	Blackout B1	2	89 / 127 / 2300	420	0,5		>6			0%	16%	84%
2220	Blackout B1	2	89 / 127 / 2450	340	0,4		>6			0%	16%	74%
2480	Marrakesch	2	2000	265	0,4		5-6			0%	54%	46%
2481	Marrakesch	2	2000	265	0,4		5-6			0%	72%	28%
2482	Marrakesch	2	2000	265	0,4		5-6			0%	34%	66%
2483	Marrakesch	2	2000	265	0,4		5-6			0%	91%	9%
2484	Marrakesch	2	2000	265	0,4		5-6			0%	58%	42%
2485	Marrakesch	2	2000	265	0,4		5-6			0%	55%	45%
2486	Marrakesch	2	2000	265	0,4		5-6			0%	53%	47%
2487	Marrakesch	2	2000	265	0,4		5-6			0%	85%	15%
2650	La Paz	2	2400/3050	340	0,48		min. 6-7			0%	21%	79%
2651	La Paz	2	2400/3050	340	0,48		min. 6-7			0%	20%	80%
2652	La Paz	2	2400/3050	340	0,48		min. 6-7			0%	21%	79%
2653	La Paz	2	2400/3050	340	0,48		min. 6-7			0%	20%	80%
2654	La Paz	2	2400/3050	340	0,48		min. 6-7			0%	20%	80%
2655	La Paz	2	2400/3050	340	0,48		min. 6-7			0%	20%	80%
2656	La Paz	2	2400/3050	340	0,48		min. 6-7			0%	19%	81%



Dargestellte Stoffe  
**1572**

## WEITERE TECHNISCHE DATEN



Art-Nr.	Name	Preisgruppe	Stoffbreite in mm	Gewicht g/m <sup>2</sup>	Dicke in mm	schwer entflammbar	Lichtecht	Ökotex	PVC-frei	Transmission (Tv)	Absorption (Av)	Reflektion (Rv)
2657	La Paz	2	2400/3050	340	0,48		min. 6-7			0%	20%	80%
2658	La Paz	2	2400/3050	340	0,48		min. 6-7			0%	20%	80%
2659	La Paz	2	2400/3050	340	0,48		min. 6-7			0%	20%	80%
2660	La Paz	2	2400/3050	340	0,48		min. 6-7			0%	21%	79%
2661	Loreto	2	89/127/2000/2400	305	0,45		min. 5-6			0%	36%	64%
4650	Nairobi	4	89 / 127 / 3000	400	0,55		5-6			0%	19%	81%
4651	Nairobi	4	89 / 127 / 3000	400	0,55		5-6			0%	18%	82%
4652	Nairobi	4	89 / 127 / 3000	400	0,55		5-6			0%	17%	83%
4653	Nairobi	4	89 / 127 / 3000	400	0,55		5-6			0%	25%	75%
4654	Nairobi	4	89 / 127 / 3000	400	0,55		5-6			0%	19%	81%
4655	Nairobi	4	89 / 127 / 3000	400	0,55		5-6			0%	23%	77%
4656	Nairobi	4	89 / 127 / 3000	400	0,55		5-6			0%	25%	75%
5100	Trevira Blackout	5	3050	340	0,45	•	5-6	•	•	0%	18%	82%
5101	Trevira Blackout	5	3050	280	0,4	•	5-6	•	•	0%	84%	16%
5102	Trevira Blackout	5	3050	280	0,4	•	5-6	•	•	0%	92%	8%
5103	Trevira Blackout	5	3050	340	0,45	•	5-6	•	•	0%	39%	61%
5104	Trevira Blackout	5	3050	340	0,45	•	5-6	•	•	0%	66%	34%
5105	Trevira Blackout	5	3050	340	0,45	•	5-6	•	•	0%	85%	15%
5106	Trevira Blackout	5	3050	280	0,4	•	5-6	•	•	0%	94%	6%
5170	Leipzig Blackout	5	2800	300	0,45		5-6	•	•	0%	43%	57%
5171	Leipzig Blackout	5	2800	300	0,45		5-6	•	•	0%	56%	44%
5172	Leipzig Blackout	5	2800	300	0,45		5-6	•	•	0%	81%	19%
5173	Leipzig Blackout	5	2800	300	0,45		5-6	•	•	0%	61%	39%
5174	Leipzig Blackout	5	2800	300	0,45		5-6	•	•	0%	77%	23%